



Technical Data Sheet
Thermylene® P7-12TC-1156
12% Talc Reinforced
PP

Material Property

DESCRIPTION

This high flow performance compound has been designed for thin-walling and light-weighting of applications and is heat stabilized for high temperature applications.

GENERAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Filler Content	12	%	ISO 3451/1
Density	1.00	g/cm ³	ISO 1183A
Melt Flow	35	g/10 min	ISO 1133

MECHANICAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Tensile Strength	37	MPa	ISO 527
Flexural Strength	57	MPa	ISO 178
Flexural Modulus	2850	MPa	ISO 178
Charpy Notched 23°C	2.0	kJ/m ²	ISO 179

THERMAL PROPERTIES	VALUE	UNIT	TEST STANDARD
HDT @ 1.8 MPa	71	°C	ISO 75

Auto Approvals

NA

Always review the MSDS prior to using any of our products. The Material Safety Data Sheet for this product is available either by contacting Asahi Kasei Plastics NA Inc. or by visiting www.akplastics.com.

There are many factors which contribute to optimal processing and part production; geometry, thickness of the part, as well as application requirements that can impact dimensional tolerances and part appearance. Please contact our company for technical assistance in this area.

This technical data sheet is a summary of known information at the time of publication. The data contained herein are preliminary and may be subject to revision. The data reflects a normal range of properties for the product specified on the technical data sheet. Extra pigments, additives or combinations with other materials may alter the data. It is the responsibility of the customer to independently determine the suitability of a particular material for the intended use. Asahi Kasei Plastics NA Inc. makes no warranties, express or implied, concerning the suitability or fitness of its products for any particular use or accepts any liability in connection with this information. Asahi Kasei Plastics NA Inc. does not allow or support the use of this or any other materials we manufacture for implantation in the human body. For additional information, general guidelines, safe handling, processing and drying protocols please check out our processing guides ([online link](#)) or call (800) 444-4408.